

## Nomassol® thread technical sheet

**BRAND: NOMASSOL®**

Product: 100% PTFE sewing thread

Humidity test: 55%

Temperature test: 21 °C

Report date: June 12, 2019

Ticket	50	40	20	15
Denier(D)	1200±50	1400±50	2500±100	3000±120
Tenacity (g/d)	≥3.40	≥3.40	≥3.40	≥3.40
Tensile strength (N)	≥38.00	≥45.00	≥80.00	≥96.00
Elongation(%)	<6.00	<6.00	<6.00	<6.00
Shrinkage(260 °C/30min)(%)	≤2.50	≤2.50	≤2.50	≤2.50